




O-Ring Energized Seals

An O-ring energized seal consists of a lip seal in combination with an O-ring. This type of seal is the optimum sealing choice for static or low-speed applications and for vacuum or high-pressure applications. These radial seals can be used in either a rod or piston style application.

The seals can be designed to provide scraping/wiping actions if needed and can be designed for pressures up to 15 ksi.

CTG's experienced engineers will custom tailor a seal to fit your exact requirements, and manufacture 1 or 1,000 seals to your specifications that same day.




CTG creates O-ring energized seals to a customer's exact specifications

Design Considerations

Lip seals used alone tend to leak at low pressure because the basic design of a lip seal provides little or no lip loading. When a lip seal is energized by an O-ring, however, sealing at low pressure is greatly improved. As system pressure increases, the seal interface experiences additional force, and a leak-free seal is maintained.

For maximum seal longevity, the seal must be constructed from the correct materials for the particular application. CTG can build seals from elastomers that tolerate high or low temperatures, high pressure or high vacuum, and corrosive environments. If you are unsure which material would be best, ask us—we can help you select exactly the right material for your situation.



Cutaway of an O-ring energized seals

Applications

- High or low temperatures
- Any pressure (hard vacuum to high pressure)
- Static or low-speed applications
- Corrosive environments

Benefits

- Manufactured from custom materials to meet the exact needs of the application
- One-piece design greatly simplifies installation and replacement
- Directly replaces other types of seal in the same size gland (no re-machining or redesign required)
- Designed to resist spiral (twisting) failure
- Extremely resistant to extrusion
- Usable with comparatively large extrusion gaps
- Provides prolonged service
- Requires minimum maintenance

The following table details the materials that are commonly used to construct O-ring energized seals.

Material	Temperature Range (°F)*	Comments and Typical Uses
Nitrile (Buna-N, NBR)	-20 to 212	Highly resistant to abrasion and tearing. Nitrile is the most commonly used elastomer for sealing applications, and it is the material of choice for petroleum applications.
Hydrogenated nitrile (HNBR)	-20 to 300	Compared to nitrile, HNBR has better chemical resistance, better heat resistance, and better resistance to seal extrusion.
Ethylene-propylene (EPDM)	-60 to 250	Very resistant to ozone.
Neoprene	-40 to 250	Resists both weathering and exposure to petroleum oils.
Butyl (isobutylene, IIR)	-50 to 250	Extremely low gas permeability; resists a diverse range of chemicals. Useful in applications requiring an air-tight seal.
Viton® (fluorocarbon, fluoroelastomer)	-15 to 400	Better resistance to chemicals and high temperatures than most other elastomers.
Silicone (VMQ, PVMQ)	-150 to 400	Excellent tolerance for temperature extremes, and high resistance to compression set.
Fluorosilicone (FVMQ, FK)	-75 to 400	Tolerant to temperature extremes, and resists degradation by fuel and oils. Primarily used where resistance to hot, dry conditions is required.
FFKM (perfluoroelastomer)	-15 to 600	Highly resistant to many chemicals, and outstanding resistance to high temperatures.
PTFE	-400 to 450	Highly resistant to many chemicals, and can function over a very wide temperature range. Also resists weathering.

*Temperature ranges given here are approximate; the values relevant to any particular situation depend upon the application. If in doubt, ask us—we will help you design an O-ring energized seal to meet the temperature tolerance needs of your system.

To discuss your application, give us a call!



ctgsales@ctgasket.com

Address: 12308 Cutten Road | Houston, Texas US | 77066

US Toll Free: 1.800.299.1685

© CTG Inc., 2016. All rights reserved.

Trademarked brand or product names mentioned in this document are the property of their respective owners.

Although reasonable effort has been made to ensure that the information in this document is accurate, it is subject to change at any time without notice. CTG assumes no liability resulting from errors or omissions in this document. Data is provided for general illustrative purposes only; it is not to be used to create specification sheets for particular parts that CTG manufactures. It is the customer's responsibility to confirm that a selected material is appropriate for a particular situation, and to evaluate parts before using them. Furthermore, because elastomeric parts have a finite lifetime, CTG strongly recommends that customers inspect such parts frequently and replace them when necessary.